

PRV

PATENT- OCH REGISTRERINGSVERKET
Patentavdelningen

Rec'd PCT/PTO 07 DEC 2004

PCT/SE 03 / 0 1 0 17

10/517226

**Intyg
Certificate**

Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.

This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.



(71) Sökande Amersham Biosciences AB, Uppsala SE
Applicant (s)

(21) Patentansökningsnummer 0202016-2
Patent application number

(86) Ingivningsdatum 2002-06-27
Date of filing

REC'D 03 JUL 2003

WIPO PCT

Stockholm, 2003-06-25

*För Patent- och registreringsverket
For the Patent- and Registration Office*

Sonia André
Sonia André

Avgift
Fee

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

**PATENT- OCH
REGISTRERINGSVERKET
SWEDEN**

Postadress/Address
Box 5055
S-102 42 STOCKHOLM

Telefon/Phone
+46 8 782 25 00
Vx 08-782 25 00

Telex
17978
PATOREG S

Telefax
+46 8 666 02 86
08-666 02 86

POLYMERIC SUPPORT HAVING NOVEL PORE STRUCTURES

Technical field

The present invention relates to the preparation of cross-linked polymeric supports that are useful e.g. in separation methods, and more specifically to a method of producing a cross-linked polymeric support useful as a chromatographic matrix, which support exhibits a novel pore structure. The invention also encompasses porous cross-linked polymeric supports as such as well as a method of modifying such supports with functional groups useful as ligands in chromatography.

Background

Cross-linked, porous polymeric supports, such as particles, are useful as adsorbents in methods for separation and purification of organic and inorganic materials, such as in chromatographic separation and filtration methods. Further applications of such supports are e.g. as microcarriers for cell culture and as supports for solid-phase peptide or DNA synthesis. The supports should be chemically compatible to organic solvents over a wide range of pH and should have a desired shape, size, and porosity and surface area.

The porosity, and the nature of the pores, are properties that have been shown to be of specific importance in chromatographic methods for purification of target molecules, since an increased porosity will result in an increased surface area and accordingly a potentially increased binding capacity.

Furthermore, a general problem in chromatography, adsorption processes, heterogeneous catalysis etc where porous particles are used, is that the mass transport rate is strongly dependent on the particle size. Rapid mass transport can be achieved by decreasing the particle size, but small particles will also increase the backpressure of the packed beds. Hence, a trade-off must be made between

the mass transport rate and the pressure-flow properties. One way to improve the mass transport in a porous particle is to increase the total pore surface. Hierarchical pore structures have for example been suggested, wherein large feeder pores from the particle surface open into a network of smaller pores with a large surface available for adsorption.

One way of providing such a pore system has been disclosed by EP 0 222 718 (Mosbach and Nilsson), which suggests to solve the above-discussed mass transport problem by introducing cavities in their particles. More specifically, EP 0 222 718 discloses a method, wherein a solid cavity-generating compound is added to an aqueous solution comprising a matrix material, emulsifier is added, particles are formed by dispersion and finally said cavity-generating compound is leached out to leave behind cavities in the particles. An illustrative cavity-generating compound is calcium carbonate, and an illustrative added amount thereof is up to 10% by weight, corresponding to 3.6 % by volume. However, at such low amounts of cavity-forming compound, the pores will not make contact with each other, resulting in a closed-cell porous structure.

A specific technology for creating very small cavities in a polymer particle using a removable target compound is known as molecular imprinting. As the name implies, molecules are used as targets and are more specifically coupled to a polymeric chain via hydrogen bonding. The molecules used are for example drug targets, such as alkaloids, and the cavity left can be described as an imprint of the used target molecule and is accordingly limited to isolation of that same molecule kind. Moreover, molecular imprinting is limited to applications wherein microdimensional pore systems are desired.

USP 5,895,263 (Carter et al) discloses how materials degradable by heating can be used in a process for forming an integrated circuit device. Porous organic polysilica, which is a dielectric material, is first dissolved in a solution of a

decomposable polymer. The mixture obtained is heated in order to condense the organic polysilica. Finally, the decomposable polymer is decomposed uniformly, e.g. by exposure to radiation, within the matrix of the condensed rigid organic polysilica. The product obtained has improved mechanical toughness, crack resistance and dielectric properties. Consequently, the product can also be used as a protective coating for optical articles, such as glasses, contact lenses and solar reflectors.

WO 01/09204 (Symyx Technologies) discloses a method of producing controlled-architecture polymers. More specifically, the disclosed architected polymers are comprised of polyacrylamide repeating units having properties that are advantageous in electrophoretic separation systems, since the sieving capability of the partially branched or cross-linked polymer will be enhanced as compared to linear non-cross-linked polymers having the same repeating unit. However, sieving is not an essential property for polymer supports intended for use as chromatographic matrices, since other properties such as the above-discussed available surface area and mass transport are then of much greater importance. The method utilises living-type or semi-living type free radical polymerisation.

At the moment, free radical suspension polymerisation is the most widely used technique in the preparation of synthetic polymer supports for heterogeneous catalysts, ion exchange resins, chromatography media, peptide synthesis etc. Pore structures are then mainly provided by incorporation of a porogen and/or control of the level of cross-linking in the resin.

Atom transfer radical polymerisation (ATRP), which is a metal/ligand catalysed polymerisation, has offered a relatively new perspective on the synthesis of polymeric resins. One of the advantages with ATRP is that it provides a high degree of control over the polymerisation process. USP 5,763,548 (Maty-

jaszewsk et al) describes in detail conditions and components used in an ATRP process for preparing plastics, elastomers, adhesives, emulsifiers, or thermo-plastic elastomers.

Summary of the present invention

One object of the present invention is to provide a method of producing cross-linked polymeric supports of multimodal pore structures. This can be achieved by a method as defined in claim 1 and the claims dependent thereon.

Another object of the invention is to provide a method of producing porous cross-linked polymeric supports, which enables the definition of the morphology of the supports produced. This can be achieved by use of a method as described above, wherein the amount and/or nature of initiator molecule is carefully controlled. Alternatively or additionally, this can be achieved by controlling the composition of the monomer feed to the polymerisation process.

A further object of the present invention is to provide porous cross-linked polymeric supports with pendant functionalities.

Yet another object of the invention is to provide porous cross-linked polymeric supports that have different functionalities on the support surface, in the primary pore system and on the surface within the larger secondary pore system.

Further embodiments and advantages of the present invention will appear from the detailed description and the experimental part below.

Brief description of drawings

Figure 1 illustrates how an organic droplet phase is polymerised by suspension polymerisation and subsequently transformed into a polymer particle comprising a secondary pore structure in accordance with the present invention.

Figure 2 shows schematically how the secondary pore structure produced according to the present invention can be surface modified.

Figure 3 shows schematically how the primary pore structure produced according to the present invention can be surface modified.

Figure 4 shows FTIR spectra of (a) beads A4; (b) beads B4; (c) beads E4; (d) beads F4; (e) beads G4; (f) beads H4.

Figure 5 shows FTIR spectra of (a) beads A4; (b) beads C4; (c) degradation product of C4; (d) beads B4; (e) beads.

Figure 6 is a SEM photograph of a cross-section of beads A1.

Figure 7 is a SEM photograph of a cross-section of beads B1.

Figure 8 is a photograph of beads A1 obtained by optical light microscopy.

Figure 9 is a photograph of beads B1 obtained by optical light.

Figure 10 shows Table 1, naming polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA.

Figure 11 shows Table 2, illustrating the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads.

Definitions

The term "initiator molecule" means herein an organic compound that comprises at least one site from which a radical polymerisation can be initiated. The term includes initiator molecules of different sizes, such as lower molecular compounds, including dimers, trimers and oligomers, and macromolecules. The term "multi-initiator" is used herein for an initiator molecule that comprises two or more initiator sites.

The term "macroinitiator" means herein an initiator molecule, which is a macromolecule and which comprises at least one initiating site.

The term "macromolecule" means herein a molecule that comprises a large number of monomeric units and has a number average molecular weight (M_n) of at least about 500.

The term "degradable" means in the present context that it is possible to remove by chemical or physical degradation thereof.

The term "multimodal" pore structure means a structure that can be created in two or more modes, such as pore systems of differing sizes and/or pore systems created at different times.

The term "support": as used herein means a matrix suitable for use as a carrier of functional groups in an isolation process, such as a chromatographic procedure. The term "support" includes particles, monoliths and membranes.

The term "dendritic" compound is used in its conventional meaning to denote an isotropically soluble polymer that exhibits a tree-like structure.

The term "porogen" refers to an inert solvent (low molecular weight or polymeric), or a mixture of inert solvents, which is present during a polymerisation reaction wherein it gives rise to formation of a porous polymer at some stage during the polymerisation.

Detailed description of the invention

A first object of the present invention is a method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of

- (a) providing a degradable initiator molecule;
- (b) providing an organic phase, which comprises said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent, and an aqueous phase, which comprises a transition metal catalyst;
- (c) forming a suspension of the organic phase and the aqueous phase;
- (d) starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and

- (e) subjecting the support obtained from step (d) to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.

Thus, the present method uses the principles of atom transfer radical polymerisation (ATRP) in an otherwise conventional suspension polymerisation process. For a general description of ATRP, see e.g. Wang et al. (in J. Am. Chem. Soc., 1995, 36, 2973; and in Macromolecules, 1995, 28, 7572). In brief, in ATRP, the initiation system is based on the reversible formation of growing radicals in a redox reaction between various transition metal compounds and an initiator. The present invention suggests for the first time to use atom transfer radical polymerisation in the production of polymeric supports that are porous. The multimodal pore structure including primary and secondary pores obtained according to the present method renders the supports especially useful as matrices in chromatographic methods.

In one embodiment of the present method, the initiator molecule provided in step (a) is obtained from commercial sources. For example, low molecular initiator molecules, such as 1-phenylethyl chloride or ethyl 2-bromoisobutyrate, are available e.g. from Acros or Aldrich. The initiator molecules can be inorganic or organic molecules, but are preferably organic compounds. In the present method, step (a) is understood to provide either one kind of initiator molecule or a mixture of two or more different initiator molecules.

In an alternative embodiment, step (a) comprises reacting a compound that has at least one hydroxy group, primary amine group or secondary amine group with an α -haloacyl halide. Thus, the reaction is either an esterification or an amidation performed according to conventional methods. An illustrative example of a suitable α -haloacyl halide is 2-bromoisobutyryl bromide (BiB),

which is commercially available e.g. from Aldrich. More examples of alfa-haloacyl halides are e.g. 2-bromopropionyl bromide, 2-bromo-iso-valeryl bromide and 2-bromo-iso-butyryl chloride.

In one embodiment, the initiator molecule provided in step (a) is a macroinitiator. Macroinitiators useful in the present invention can have virtually any three-dimensional structures, such as a dendritic structure, including star-shaped and hyperbranched structures.

In an advantageous embodiment, the initiator molecule is synthesised by reacting a hydroxy-functional dendritic polyester with an alfa-haloacyl halide, resulting in a polyester macroinitiator. Hydroxy-functional polyesters are commercially available, e.g. Boltorn® from Perstorp Chemicals AB (Sweden), which is available in five generations and thus offers a convenient variety in size of the secondary pores created by their removal with little change in chemistry.

Dendritic polyesters useful as starting materials in the synthesis of a macroinitiator can also be prepared as described in WO 93/17060 (Hult et al) or WO 99/00440 (Ihre et al).

In an alternative embodiment, the initiator molecule is synthesised by reacting an amino-functional dendritic polyamide with an alfa-haloacyl halide, resulting in a polyamide macroinitiator. Amino-functional polyamides can for example be prepared as described in Tomalia et al (Angew. Chem. Int. Ed. Engl. 29, p. 138-175), describing the preparation of dendritic polyamide amines.

In one embodiment, the initiator molecule used in the present method can be prepared in the desired size by reacting a specified generation of a dendritic initiator molecule with an alfa-haloacyl halide. As mentioned above, some

commercially available starting materials such as Boltorn® are available in several generations. Similarly, the synthesis of polyesters and/or amides can be performed in order to provide the desired generation of the dendritic molecule. Thus, one advantage with the present method is that by carefully selecting the size of the initiator molecule, the secondary pore size in the final product can be controlled. Thus, the novel kind of pores that is provided by removal of the initiator molecule can be defined by the size of the initiator molecule used. In addition, the novel pores can also consist of interlinks between the more conventional primary pores that originate from the porogen and/or monomer composition. Both the cavities formed where the initiator molecule is removed and the above-mentioned interlinks are part of the secondary pore structure, which is a kind of pore structure that cannot be achieved under conventional suspension polymerisation conditions.

Furthermore, even though the above-discussed USP 5,763,548 describes the principles of atom transfer radical polymerisation (ATRP), the conditions defined therein do not correspond to a conventional suspension polymerisation, such as the suspension polymerisation utilised according to the present invention. Furthermore, USP 5,763,548 describes ATRP for the preparation of solid articles, such as plastics, elastomers and the like, and nothing therein suggests that ATRP would be especially advantageous for the purpose of preparing porous polymeric supports. Accordingly, the present invention utilises for the first time the principles of ATRP with suspension polymerisation. In addition, the present invention combines such a polymerisation with the use of a degradable initiator molecule in order to provide a bimodal pore structure in the product.

The organic phase can be prepared in any suitable solvent, or mixture of solvents, conventionally used for suspension polymerisation, such as toluene, hexanone etc.

In one embodiment, the organic phase comprises up to 50%, such as about 30%, e.g. 32%, of initiator molecule, calculated as weight initiator molecule/weight main monomer. However, as the skilled person in this field will realise, the upper limit of the initiator molecule that can be provided in the organic phase will depend on the nature of the further components. For example, if a monomer feed that results in a more rigid polymer structure is used, then the proportion of initiator can be higher, the upper limit being determined by the risk of collapse of the final product. Accordingly, the intended use of the polymeric support produced will also be a factor to consider when the proportions of the components of the organic phase are decided.

The monomers present in the organic phase should provide for both polymerisation and cross-linking and the only requirement thereof is that they should be radically polymerisable. As is easily realised, in order to obtain a cross-linked product, at least one monomer present in the organic phase needs to be multifunctional. Thus, in one embodiment, the monomers are synthetic mono and/or multifunctional monomers, such as styrene and/or divinyl benzene.

In an advantageous embodiment, the organic phase also comprises one or more functional monomers, i.e. monomers that firstly comprise one vinyl group, which will be able to participate in the polymerisation, and secondly another functional group, which is not a vinyl group. Such a non-vinyl functional group can e.g. be a hydroxyl, an amine, or any other group that can subsequently be used for other purposes than forming the polymeric structure of the support.

The skilled person who uses the method according to the invention can easily decide what kind of further functionalities that are needed for each intended purpose. One illustrative such further functionality is an easily accessible chemical handle for further derivatisation of supports intended for use as chromatographic matrices.

In the present context, the term "bulk monomers" is used for the monomers that are added in large amounts to contribute to the basic polymeric structure of the support.

Mixtures of different monomers can also be provided in the organic phase.

Examples of useful monomers are also illustrated in the above-discussed USP 5,763,548.

Finally, in order to obtain the primary pore structure, the organic phase also comprises a conventional porogen. In a convenient embodiment, the solvent also acts as a porogen. Suitable porogens for use in this context are well known in this field, and the skilled person can easily make a selection among the commercially available products. As the skilled person in this field will realise, the primary pore structure will also be affected by components of the monomer feed.

Any transition metal compound that can participate in a redox cycle with the initiator and dormant polymer chain, but which does not form a direct carbon-metal bond with the polymer chain, is suitable for use in the present method. Thus, in one embodiment, the transition metal present in the catalyst is selected from the group that consists of Cu, Ni, Pd, Ru and Fe. In a preferred embodiment, the transition metal is copper (Cu), such as Cu(I) or Cu(II).

Suitable ligands for use in the present invention include ligands having one or more nitrogen, oxygen, phosphorous and/or sulphur atoms that can co-ordinate to the transition metal through a sigma-bond; ligands that contains two or more carbon atoms that can co-ordinate to the transition metal through a π -bond; and ligands that can co-ordinate to the transition metal through a μ -bond or an η -bond. Accordingly, in one embodiment, the ligand comprises one or more N, O, P, S or C atoms that co-ordinate to the transition metal in the catalyst. In a spe-

cific embodiment, the ligand is N,N,N',N',N''-pentamethyldiethylenetriamine. As the skilled person in this field will realise the catalyst will be comprised of a transition metal complexed to a ligand, which complexing will take place more or less immediately after the ligand has been added to the suspension. For this reason, it is preferred to allow a relatively stable suspension to form before adding the ligand. As is well-known in this field, if the reaction is to be scaled-up to a suspension polymerisation reactor, then it is common to adjust the organic droplet size to roughly the size of the desired particles. Thus, in this case, it is preferred to adjust stirrer speed, allow droplet size to stabilise, readjust stirrer speed etc before adding the ligand. Accordingly, in the most advantageous embodiment, step (d) is performed a suitable period of time after step (c), e.g. after about 1 h. In this context, it is also noted that the ligand, which is water-soluble, should in some cases not be present in the aqueous phase before it is contacted with the organic phase, since it will then result in an immediate start of the polymerisation as soon as the two phases are contacted. In an alternative embodiment, the metal catalyst should not be present. As the skilled person in this field will realise, the factors that decides whether or not polymerisation will start immediately is the temperature and the nature of the monomers, hence the conditions are easily adapted from case to case to ensure that the polymerisation is not started until appropriate. This should be avoided, especially in cases where spherical particles are desired.

As mentioned above, the present method is performed under conditions that correspond to any conventional suspension polymerisation (for the basic principles of conventional suspension polymerisation, see e.g. J. R. Benson and D. J. Woo, J. Chromatographic Sci., 1984, 22, 386). Accordingly, the polymerisation can be performed at virtually any temperature below that where a substantial part of the aqueous phase will evaporate or the organic phase will boil. Thus, the temperature may e.g. be ambient temperature, and the reaction time can be

any period of time between about 5 minutes and up to several days, such as overnight.

The polymerisation is started according to step (d) by addition of a ligand that co-ordinates to the transition metal, whereby a catalyst is formed. The amount of ligand and transition metal used in the present method are those effective to conduct ATRP, see e.g. USP 5,763,548. More specifically, the molar proportion of ligand relative to the transition metal is generally that which is effective to polymerise the selected monomer(s), but can depend on the number of co-ordination sites on the transition metal which the ligand will occupy. The amount of ligand may be selected such that the ratio of (i) co-ordination sites on the transition metal to (ii) co-ordination sites, which the ligand will occupy, is from 0.1:1 to 100:1, such as 0.8:1 to 2:1.

In one embodiment, the removal according to step (e) is performed at basic or acidic conditions. Thus, a change of the pH in the environment can degrade the initiator molecule within the polymeric support. In another embodiment, the removal is performed by degradation of the initiator molecule by applying an external agent, such as heat and/or radiation and/or ultrasound. As the skilled person in this field will realise, the degrading conditions are dependent on the nature and chemical structure of the initiator molecule used. For example, a dendritic polyester macroinitiator can be removed by basic hydrolysis, as illustrated in the examples below. The results can be evaluated by any conventional method, such as Fourier transform infrared spectrometry (FTIR), titration and/or gravimetry. In a specific embodiment of the present method, the removal of the initiator molecule is quantitative. This can be advantageous as a control measure in cases where it is essential to confirm that no initiator molecule has been left in the polymeric support produced, e.g. in various bioprocesses, especially in the pharmaceutical field.

In an especially advantageous embodiment, the present method is used to produce cross-linked porous polymeric supports comprising one functionality or property within primary pores and the same or a different functionality or property within secondary pores. The method then comprises the method as described above and an additional step of selective surface modification of the supports so obtained after step (d) but before step (e). Such surface modification can for example be to introduce functional groups at chemical handles introduced as described above, which functional groups advantageously are ligands useful in chromatography, such as affinity groups, ion exchange groups or the like. Alternatively, the purpose of the surface modification can be to provide the surface of the primary pores with another property, such as hydrophobicity or hydrophilicity. Thus, in one embodiment, the surface available of the support obtained from step (d) is modified using acidic, neutral or basic conditions. The only requirement here is that the conditions used should not degrade the initiator molecule, unless the same modification is desired within both the primary and secondary pores.

The surface of the cavities left after removal of the initiator molecule according to step (e) will be provided with pendant groups resulting from breaking the bond of the ester or amide of the initiator molecule. In the case where the initiator molecule has been removed by hydrolysis, the pendant groups can for example be carboxylic groups. The pendant groups can after step (e) be converted, for example by reduction of carboxyl groups to yield hydroxyl or ether groups, by azido-decarboxylation and subsequent hydrolysis to yield amine groups. Alternatively, the pendant groups can be used to support ligands useful in chromatographic applications, in which case treatment with e.g. SOCl_2 is followed by addition of ligand-hydroxyl groups or ligand-amine groups. In another embodiment, the surface of the cavities can be treated as discussed above in order to change its properties, e.g. to make it more hydrophobic or hydro-

philic. In a further embodiment, the surface is modified by polymerisation of linear or cross-linked polymer.

Accordingly, the external surface of the supports, the surface of the primary pores and the surface of the pores obtained after removal of the initiator molecule can be modified in any suitable way, depending on the desired use.

As mentioned above, in one embodiment of the present method, the secondary pore size is controlled by using an initiator molecule of a suitable molecular weight. Naturally, the larger initiator molecule used, the larger secondary pores will be obtained. In this context, it is essential to bear in mind that the polymeric supports must be sufficiently robust to not break during step (e).

A second aspect of the present invention is cross-linked porous polymeric support, which exhibits the above-described primary and secondary pore structure. Thus, in one embodiment, the polymeric support has been produced according to the method described above. In a specific embodiment, the polymeric support according to the invention is an essentially spherical particle having a diameter of about 10μ - 250μ and wherein the absolute surface area is in a range of 150 - $500\text{ m}^2/\text{g}$, such as $300\text{ m}^2/\text{g}$. The particles according to the invention are advantageously used as matrices in chromatography, where the large surface area thereof will increase their binding capacity as compared to prior art matrices. Also, the novel multimodal pore structure will contribute to improved mass transport properties.

However, for some isolation purposes columns packed with polymer particles are unsuitable because of the high level of back pressure created. Accordingly, in an alternative embodiment the support according to the invention is a monolith, such as a monolithic plug. The monolith has open passages therethrough, such as a honeycomb-shaped structure, and is desirable for applications

wherein a reasonably high rate of fluid flow and a low level of backpressure are required.

In an alternative embodiment, the support according to the invention is a membrane. Such a membrane will include a layer of polymeric support according to the invention fixed onto or attached to a base material according to well-known principles. Membranes are especially advantageous e.g. for large-scale operation, where high flow rates and high capacities are desired.

In an advantageous embodiment, the polymer particle according to the invention comprises one or more kind of chromatography ligands selected from the group affinity ligands, ion exchange ligand, etc bound to the surface of the primary pores and/or the secondary pores. In one embodiment, the surface of the primary and/or secondary pores has been rendered hydrophobic. In an alternative embodiment, the surface of the primary and/or secondary pores has been rendered hydrophilic.

The support according to the invention is accordingly useful for almost any isolation process wherein one or more target substances are separated from other components in a liquid. Thus, the support according to the invention can be used as a chromatographic adsorbent for isolation or separation of biomolecules, such as proteins, nucleic acids, such as plasmids, DNA or RNA, viruses etc, of other organic molecules, such as drug candidates, carbohydrates, or any inorganic compounds or molecules, depending on how they are modified. Similarly, the present method is also useful for purification of a liquid, from which removal of one or more of the above-exemplified target substances is desired. Thus, apart from the purification of a target compound or a liquid, the present invention is also useful for example in methods of combinatorial chemistry. The support according to the invention can also be used as a micro-

carrier for cell culture and as supports for solid-phase peptide or DNA synthesis.

A third aspect of the present invention is the use of a polymeric support according to the invention as a matrix in chromatography. The principles of different chromatographic separation methods, such as ion exchange chromatography, affinity chromatography, hydrophobic interaction chromatography etc are well known and have been thoroughly described in literature.

Detailed description of the drawings

Figure 1 (a) to (c) is a schematic drawing showing how an organic droplet phase (a) is polymerised by suspension polymerisation into a polymer particle (b) comprising a primary pore structure with areas of initiator molecule (dark areas), which is subsequently transformed into a polymer particle comprising a secondary pore structure (c) by removal of said initiator.

Figure 2 shows schematically some examples of possible surface modification of the secondary pore structure produced by removal of the initiator molecules according to the present invention. More specifically, a particle comprising an dendritic polyester (Boltorn®) and divinylbenzene is treated so that differing internal and external functionalities are obtained after hydrolysis.

Figure 3 shows schematically how the primary pore structure produced according to the present invention can be surface modified.

Figure 4 shows FTIR spectra of (a) beads A4; (b) beads B4; (c) beads E4; (d) beads F4; (e) beads G4; (f) beads H4 as described in detail in the examples below.

Figure 5 shows FTIR spectra of (a) beads A4; (b) beads C4; (c) degradation product of C4; (d) beads B4; (e) beads D4 as described in detail in the examples below.

Figure 6 is a A SEM photograph of a cross-section of beads A1 as described in detail in the examples below, see specifically example 2.

Figure 7 is a SEM photograph of a cross-section of beads B1 as described in detail in the examples below.

Figure 8 is a photograph of beads A1 obtained by optical light microscopy as described in detail in the examples below.

Figure 9 is a photograph of beads B1 obtained by optical light microscopy as described in detail in the examples below.

Figure 10 shows Table 1, naming polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA, see example 2 below.

Figure 11 shows Table 2, illustrating the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads, see example 3 below.


9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100

EXPERIMENTAL PART

Below, the present invention will be described in more detail by way of examples, which however are in no way intended to limit the scope of the present invention as defined by the appended claims. All references given below or elsewhere in the present specification are hereby included herein by reference.

Example 1: General procedure for the preparation of the polyester macroinitiators

Example 1-1: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G2-BiB




Boltorn® G2-BiB

Boltorn® G2 (3.50 g; 2 mmol), triethylamine (4.86 g; 48 mmol) and 4-(N,N-dimethylamino)pyridine (1.95 g; 16 mmol) were dissolved in dichloromethane (40 ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (8.83 g, 38.4 mmol) was dissolved in dichloromethane (10 ml) and added dropwise to the aforementioned solution. The reaction was allowed to proceed at room temperature overnight. The organic phase was extracted first with aq. NaHCO₃ (10%) and then with aq. NH₄Cl (10%). The organic phase was dried over MgSO₄, clarified with carbon black, and the solvent was removed under vac-

uum to give the product as pale-yellow oil. Yield 6.2 g (75%). FTIR (film/NaCl) ν_{max} (cm^{-1}) 2980, 1740, 1273, 1162, 766. ^1H NMR (CDCl_3): δ_{H} (ppm) 1.20-1.40 (m, 36H, CH_3 , Boltorn®), 1.91(s, 96H, CH_3 , BiB), 3.30-3.80 (m, 20H, CH_2), 4.30-4.40 (m, 56H, CH_2). ^{13}C NMR (CDCl_3): δ_{C} (ppm) 18, 31, 47, 55, 66, 171, 172.

Example 1-2: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G3-BiB




Boltorn® G3-BiB

Boltorn® G3 (10.0 g; 1.4 mmol) and triethylamine (13.4g; 67 mmol) were dissolved in tetrahydrofuran (30 ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (24.5 g, 53 mmol) was dissolved in tetrahydrofuran (24 ml) and added dropwise to the aforementioned solution. The reaction was allowed to proceed at room temperature for 3 hours. The solution was acidified with aq. HCl (37%) and filtered to remove triethylamine salts. The solvent was removed under vacuum and the resulting oil dried by coevaporation with toluene. The oil was dissolved in dichloromethane, the solution clarified with carbon black and filtered. The solvent was evaporated under vacuum. The crude

product was dissolved in a minimum amount of dichloromethane and precipitated into n-hexane. This operation was repeated until no impurities were detected by ^1H NMR. The solvent was then removed under vacuum to give a pale-yellow solid. Yield 16.7g (72%). FTIR (film/NaCl) ν_{max} (cm^{-1}) 2980, 1740, 1273, 1162, 766. ^1H NMR (CDCl_3): δ_{H} (ppm) 1.20-1.40 (m, 84H, CH_3 , Boltorn®), 1.91(s, 192H, CH_3 , BiB), 3.30-3.80 (m, 20H, CH_2), 4.30-4.40 (m, 120H, CH_2). ^{13}C NMR (CDCl_3): δ_{C} (ppm) 18, 31, 47, 55, 66, 171, 172.

Example 1-3: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G4-BiB



Boltorn® G4-BiB

Boltorn® G4 (10.4 g; 0.68 mmol) and triethylamine (13.2 g; 66 mmol) were dissolved in dichloromethane (30ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (24.0 g, 52 mmol) was dissolved in dichloromethane (20 ml) and added dropwise to the aforementioned solution. The reaction was

allowed to proceed at room temperature for 3 hours. Dichloromethane was added to the reaction and the organic phase was extracted first with aq. HCl (2M) and then with aq. NaHCO₃(10%). The organic phase was dried over MgSO₄, clarified with carbon black, and the solvent was removed under vacuum. The resulting oil was dissolved in a minimum amount of dichloromethane and precipitated into n-hexane. This operation was repeated until no impurities were detected by ¹H NMR. The solvent was then removed under vacuum to give a pale-yellow solid. Yield 15.9 g (69%). FTIR (film/NaCl) ν_{\max} (cm⁻¹) 2980, 1740, 1273, 1162, 766. ¹H NMR (CDCl₃): δ_H (ppm) 1.20-1.40 (m, 180H, CH₃, Boltorn®), 1.91(s, 384H, CH₃, BiB), 3.30-3.80 (m, 20H, CH₂), 4.30-4.40 (m, 248H, CH₂). ¹³C NMR (CDCl₃): δ_C (ppm) 18, 31, 47, 55, 66, 171, 172.

Example 2: General procedure for the preparation of polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA (Fig 10, Table 1)

Divinylbenzene and Boltorn®-BiB macroinitiator were dissolved in toluene in a screw-top test tube. Ethyl-1-hexanol was added to the solution. The aqueous phase was made-up by combining an aqueous solution of Mowiol 40-88 with CuCl and aq. HCl. The aqueous phase was added to the vial and a suspension was created by shaking the vial. N,N,N',N',N''-pentamethylthriethylenediamine was added and the vial was shaken vigorously. The suspension was maintained for 24 hours at room temperature by rotating the vial at 60 rpm perpendicular to a parallel axis. The content of the vial was poured into boiling water. The beads were removed by filtration and washed with boiling water, ethanol and acetone. The beads were dried overnight under vacuum at 75 °C.

Example 2-1: Preparation of polydivinylbenzene beads initiated by Boltorn® G3-BiB and mediated by CuCl/PMDETA (Beads A4)

Divinylbenzene (4.90 ml; 4.48 g; 34.4 mmol) and Boltorn® G3-BiB (2.11 g; 0.25 mmol) were dissolved in toluene (2.10 ml) in a 50 ml screw-top glass test tube. 2-Ethyl-1-hexanol (4.90 ml) was added to the solution. The aqueous phase was made-up by combining an aqueous solution of Mowiol 40-88 (5%) (36 ml) with CuCl (0.24 g, 2.42 mmol) and aq. HCl (37%) (0.21 ml). The aqueous phase was added to the vial and a suspension was created by shaking the vial. N,N,N',N',N''-pentamethylthriethylenediamine (1.00 ml, 0.83g, 4.79 mmol) was added and the vial was shaken vigorously. The suspension was maintained for 24 hours at room temperature by rotating the vial at 60 rpm perpendicular to a parallel axis. The content of the vial was poured into boiling water (1000 ml). The beads were removed by filtration and washed with boiling water (8000 ml), ethanol (500 ml) and acetone (200 ml). The beads were dried overnight under vacuum at 75 °C. Yield 5.42 g (82%). FTIR (KBr) ν_{\max} (cm⁻¹) 3004 ((C-H)_{Ar}), 2965 ((C-H)_{CH3}), 2926 ((C-H)_{CH2}), 1740 (C=O), 1628 (C=C)_{vinyl}, 1596 (Ar-breathing), 1273-1162 (C-O-C) (Figure 4).

A SEM photograph of a cross-section of beads A1 is given as example in Figure 6.

A microphotograph of beads A1 obtained by optical light microscopy is given as example in Figure 8. Spherical beads being 10 - 60 µm i.d. were obtained.

Example 3: General procedure for the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads (Fig 11, Table 2)

The poly(Boltorn®-BiB-divinylbenzene) beads were shaken in ethanolic NaOH (10%) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed successively with ethanolic NaOH (10%), water, ethanol, ethanolic HCl (2 M), ethanol and acetone, and dried under vacuum at 75 °C.

Example 3-1: Hydrolytic degradation of beads A4 (Beads B4)

The poly(Boltorn®-BiB-divinylbenzene) beads A4 (0.1422 g) were shaken in ethanolic NaOH (10%) (20 ml) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed with ethanolic NaOH (10%) (100 ml), water (1000 ml), ethanol (500 ml), ethanolic HCl (2 M) (500 ml), ethanol (500 ml) and acetone (200 ml) and dried under vacuum at 75 °C. Yield 0.1033 g. FTIR (KBr) ν_{max} (cm⁻¹) 3030 and 3004 ((C-H)_{Ar}), 2926 ((C-H)_{CH2}), 1720-1700 (C=O), 1628 (C=C)_{vinyl}, 1596 (Ar-breathing) (Figure 4).

A SEM photograph of a cross-section of beads B1 is given as example in Figure 7.

A microphotograph of beads B1 obtained by optical light microscopy is given as example in Figure 9. Spherical beads being 10 - 60 µm i.d. were obtained.

Example 4: ATRP of MMA

Beads, MMA, transition metal, ligand and solvent were combined and degassed with a N₂ stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane, ethanolic HCl (2M), ethanol and acetone. The beads were dried under vacuum at 75 °C for 24 hours.

Example 4-1: ATRP of MMA using beads A4 (Beads C4)

Beads A4 (0.1003 g), MMA (1.225 g, 12.2 mmol), CuCl (0.0118 g, 0.119 mmol), 2,2'-bipyridine (0.0380 g, 0.243 mmol) and anisole (1.308 ml) were combined and degassed with a N₂ stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane (200ml), ethanolic HCl (2M) (200

ml), ethanol (100 ml) and acetone (200 ml). The beads were dried under vacuum at 75 °C for 24 hours. Yield 0.2300g; 12.9 mmol MMA units per gram starting material. A FTIR spectrum is shown in Figure 5.

Example 4-2: ATRP of MMA using beads B4 (Beads D4)

Beads B4 (0.0408 g), MMA (0.668 g, 6.85 mmol), CuCl (0.0076 g, 0.077 mmol), 2,2'-bipyridine (0.0207 g, 0.132 mmol) and anisole (0.735 ml) were combined and degassed with a N₂ stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane (200ml), ethanolic HCl (2M) (200 ml), ethanol (100 ml) and acetone (200 ml). The beads were dried under vacuum at 75 °C for 24 hours. Yield 0.0523g; 2.82 mmol MMA units per gram starting material. A FTIR spectrum is shown in Figure 5.

Example 5: Sulphonation using beads A4 (Beads E4)

Beads A4 (5.00 g) were slurred in chloroform (25 ml). Chlorosulphonic acid (23 ml, 40.7 g, 350 mmol) was added in several portions to the reaction mixture. The reaction was shaken at room temperature overnight. The beads were filtered and washed with dichloromethane (500 ml) and acetone (200 ml). The beads were shaken overnight in aq. NaHCO₃ (10%) (50 ml). The beads were removed by filtration and washed with aq. NaHCO₃ (10%) (200 ml), aq. HCl (2M) (200ml), ethanol (200ml), acetone (200ml) and ether (100ml) and dried under vacuum at 75 °C overnight to give orange beads. Yield 5.99 g. FTIR (KBr) ν_{\max} (cm⁻¹) 3463 (S-OH), 3030 ((C-H)_{Ar}), 2965 ((C-H)_{CH3}), 2926 ((C-H)_{CH2}), 1740 (C=O), 1596 (Ar-breathing), 1211 and 1177 (O=S=O) (Figure 4).

Example 6: Chlorination of beads E4 (Beads F4)

Thionyl chloride (20 ml, 274 mmol) was added slowly to the dried beads (3.97 g) under a N_2 stream and the flask was sealed and shaken at 60 °C for 48 hours. The beads were filtered and washed with chloroform (300 ml) and dried under vacuum at 75 °C over one day to give brown/purple beads. Yield 3.94 g. FTIR (KBr) ν_{\max} (cm^{-1}) 3030 ((C-H)_{Ar}), 2965 ((C-H)_{CH3}), 2926 ((C-H)_{CH2}), 1740 (C=O), 1596 (Ar-breathing), 1371 and 1172 (O=S=O) (Figure 4).

Example 7: Synthesis of 2-(aminomethyl)pyridine sulphonamide derivative from beads F4 (Beads G4)

Beads F4 (0.4876 g) were slurried in dichloromethane (5 ml) and cooled to 0 °C. 2-(aminomethyl)pyridine (1.88 g; 17.4 mmol) was dissolved in dichloromethane (5 ml) and cooled to 0 °C. The above solution was slowly added to the beads slurry under constant shaking. The reaction was heated to 50 °C and shaken for 24 hours. The beads were removed by filtration and washed with ethanol (99.5%) (100 ml), water (100 ml), ethanol (99.5%) (100 ml), acetone (100 ml) and dichloromethane (100ml). Yield: 0.4956 g. FTIR (KBr) ν_{\max} (cm^{-1}) 3280 (N-H), 3030 and 3010 ((C-H)_{Ar}), 2965 ((C-H)_{CH3}), 2926 ((C-H)_{CH2}), 1740 (C=O), 1596 (Ar-breathing), 1327 and 1172 (O=S=O) (Figure 4).

Example 8: Hydrolytic degradation of beads G4 (Beads H4)

Beads G4 (0.1565 g) were shaken in ethanolic NaOH (10%) (20 ml) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed with ethanolic NaOH (10%) (100 ml), water (1 L), ethanol (500 ml), ethanolic HCl (2 M) (500 ml), ethanol (500 ml) and acetone (200 ml) and dried under vacuum at 75 °C. Yield 0.1275 g. FTIR (KBr) ν_{\max} (cm^{-1}) 3280 (N-H), 3030 and 3010 ((C-H)_{Ar}), 2965 ((C-H)_{CH3}), 2926 ((C-H)_{CH2}), 2800-2400 (O-H)_{acid H-bonded}, 1700 (C=O), 1596 (Ar-breathing), 1327 and 1172 (O=S=O) (Figure 4).

CLAIMS

1. A method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of
 - (a) providing a degradable initiator molecule;
 - (b) providing an organic phase, which comprises said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent, and an aqueous phase, which comprises a transition metal catalyst;
 - (c) forming a suspension of the organic phase and the aqueous phase;
 - (d) starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and
 - (e) subjecting the support obtained from step (d) to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.
2. A method according to claim 1, wherein the initiator molecule is a macro-initiator.
3. A method according to claim 1 or 2, wherein step (a) comprises to react a compound that comprises at least one hydroxy group, primary amine group or secondary amine group with an alfa-haloacyl halide.
4. A method according to claim 3, wherein a hydroxy-functional dendritic polyester is reacted with the alfa-haloacyl halide.
5. A method according to claim 3, wherein an amino-functional dendritic polyamide is reacted with the alfa-haloacyl halide.
6. A method according to any one of the preceding claims, wherein in step (d), the organic phase comprises up to about 50%, such as about 30%, of the initiator molecule, calculated as weight/weight monomer.

7. A method according to any one of the preceding claims, wherein the monomers are synthetic mono and/or multifunctional monomers, such as styrene and/or divinyl benzene.
8. A method according to any one of the preceding claims, wherein the transition metal is selected from the group that consists of Cu, Ni, Pd, Ru and Fe.
9. A method according to any one of the preceding claims, wherein the ligand comprises one or more N, O, P, S or C atoms that co-ordinated to the transition metal to form a catalyst system.
10. A method according to any one of the preceding claims, wherein the removal according to step (e) is performed under basic or acidic conditions.
11. A method according to any one of the preceding claims, wherein the removal according to step (e) is performed by applying an external agent, such as heat and/or radiation and/or ultrasound.
12. A method of producing a cross-linked polymeric support comprising one functionality within a primary pore structure and one functionality within a secondary pore structure, which comprises a method according to any one of the preceding claims and an additional step of selective surface modification of the supports so obtained after step (d) but before step (e).
13. A method according to claim 12, wherein the surface of the support obtained from step (d) is modified using conditions that have no essential impact on the initiator molecule present in the support.
14. A method according to any one of the preceding claims, wherein the secondary pore size is controlled by the molecular weight of the initiator molecule.
15. A cross-linked porous polymeric support, which has been produced according to any one of claims 1-14.
16. A polymeric support according to claim 15, which is comprised of one or more essentially spherical particles having a diameter of about 10 μ m and 250 μ m, wherein the specific surface area is in a range of 150-300 m²/g.
17. A polymeric support according to claim 15, which is a monolith.

18. A polymeric support according to any one of claims 15-17, which comprises functional groups, such as chromatography ligands, coupled to the surface of the primary pores and/or the secondary pores.
19. Use of a polymeric support according to any one of claims 15-18 as a matrix in chromatography.

ABSTRACT


The present invention relates to a method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of providing a degradable initiator molecule; providing an organic phase comprising said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent; providing an aqueous phase comprising a transition metal catalyst; starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and subjecting the support obtained to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.

The invention also relates to a support produced according to the method above, e.g. in the form of particles, a monolith or a membrane.

9
1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2



3) degradation
4) wash residues



1) polymerisation
2) wash out porogen





Figure 1.

Figure 3.



0203016-3

PRV 020627




Figure 4.





Figure 5.

0000016-2

Figure 7.



0000014-3

Figure 8.




Figure 9.




Figure 10.

Table 1: Polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA

Beads	Boltorn®-BiB		DVB (g)	Porogen		Yield (%)	Before hydrolysis	
	Generation	Mass (g)		Toluene (ml)	2-Ethyl-1-hexanol (ml)		Surface area (m ² g ⁻¹)	Adsorption pore volume (ml g ⁻¹)
A1 ^a	2 nd	0.33	0.60	0.33	0.66	86	134	0.3742
A2 ^b	2 nd	0.15	0.27	0.22	0.45	82	65	0.1872
A3 ^b	2 nd	0.30	0.27	0.30	0.30	79	1	0.0067
A4 ^c	3 rd	2.11	4.48	2.10	4.90	82	117	0.3354
A5 ^c	3 rd	1.53	3.26	1.99	4.64	81	73	0.1833
A6 ^d	4 th	0.17	0.37	0.17	0.40	94	64	0.1547
A7 ^e	4 th	0.75	1.60	0.97	2.27	91	140	0.3210

^aSealed test tube reactor, 12 ml; 9 ml Mowiol (5%), 0.03 ml HCl (37%), 0.18 ml PMDETA, 0.044 g CuCl

^bSealed test tube reactor, 5 ml; 3 ml Mowiol (5%), 0.03 ml HCl (37%), 0.092 ml PMDETA, 0.022 g CuCl

^cSealed test tube reactor, 50 ml; 36 ml Mowiol (5%), 0.21 ml HCl (37%), 1 ml PMDETA, 0.22 g CuCl

^dSealed test tube reactor, 5 ml; 3 ml Mowiol (2%), 0.03 ml HCl (37%), 0.092 ml PMDETA, 0.022 g CuCl

^eSealed test tube reactor, 25 ml; 16 ml Mowiol (2%), 0.13 ml HCl (37%), 0.46 ml PMDETA, 0.11 g CuCl

Figure 11.

Table 2: Hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads

Beads	Boltorn®-BiB		Wt% DVB	Amount of initiation sites in feed (mmol g ⁻¹)	After hydrolysis				
	Generation	Wt%			% Retention of resin ^a	Carboxylic acid group capacity (mmol g ⁻¹) ^b	% Conversion of initiation sites ^c	Surface area (m ² g ⁻¹)	Adsorption pore volume (ml g ⁻¹)
B1	2 nd	35.4	64.6	1.37	66.7	0.56	27	281	0.4955
B2	2 nd	35.4	64.6	1.37	69.8	1.35	69	142	N/A
B3	2 nd	52.2	47.8	2.02	57.4	0.80	23	90	0.0731
B4	3 rd	32.0	68.0	1.22	72.6	0.86	51	199	0.4943
B5	3 rd	31.9	68.1	1.22	80.6	0.84	56	245	0.2997
B6	4 th	31.9	68.1	1.21	71.4	0.78	46	171	0.3448
B7	4 th	31.9	68.1	1.21	79.1	0.56	36	291	0.4249

^aDetermined by gravimetry

^bDetermined by titration

^cCalculated as, (carboxylic acid group capacity/ retention of resin)/ amount of initiation sites in feed

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.